


Product	Sinopec HPXT Grease
Summary	<p>Product description</p> <p>Sinopec HPXT Grease is an extreme pressure grease formulated with an extreme pressure, heavy-duty wheel bearing and chassis grease, formulated with a lithium complex soap thickener and high-quality mineral base oil. It contains rust and oxidation inhibitors, EP and antiwear additives to ensure excellent performance and long life, even in severe service conditions such as high temperatures, shock loading and where water contamination is possible.</p>

Available sizes



Applications

Sinopec HPXT Grease is suitable for use in:

- Automotive wheel bearings, particularly those operating under the high-temperature, high-load conditions that are caused by braking at high speed.
- General lubrication of chassis points (e.g. shackles, tie rod ends, steering knuckles, control arms and king pins), electric motors and water pumps of passenger cars, buses and trucks.
- Applications requiring an NLGI GC-LB wheel bearing and chassis grease where the operating temperature range is between -30°C and +180°C.

Features and benefits

- Lithium complex soap thickener ensures a high dropping point, which means that the grease can be used at higher temperatures in severe service applications (operating temperature range is from -30°C to +180°C), and also confers excellent mechanical stability so that the grease structure does not break down in service.
- Excellent adhesive properties ensure the grease sticks to metal surfaces even under high-temperature conditions, and provides an optimum oil film thickness to protect the moving parts and provide long service life.
- Excellent extreme pressure and antiwear properties protect heavily loaded or shock-loaded bearings from wear, extending equipment life.
- Excellent water resistance means that the grease stays in place and is not washed or sprayed off in wet conditions, reducing the need for frequent re-application.
- Excellent protection against rusting and corrosion ensures long component life, and extends maintenance intervals.
- Good thermal and oxidation stability ensure longer grease life under high-temperature conditions, providing optimum lubrication, extending equipment life and reducing maintenance requirements.
- The consistency meets the requirements of wheel bearing applications, and avoids the grease being flung out of the bearing by centrifugal forces, so ensuring longer relubrication intervals.

Product Data Sheet

Typical data

Sinopec HPXT Grease	
NLGI grade	2
Appearance, visual	Smooth, blue, buttery
Thickener type	Lithium complex
Base fluid type	Mineral
Cone penetration, ASTM D 217	
W _{x60} , mm ⁻¹	286
W _{x100,000} , % change from W _{x60}	9
Dropping point, °C, ASTM D 2265	326
Oil separation, 30 h @ 100°C, %, FTMS 791C-321.3	0.8
Four ball wear, 60 min @ 392 N, mm, ASTM D 2266	0.44
Timken OK load, N, ASTM D 2509	178
Water washout, 1 h @ 79°C, %, ASTM D 1264	2
Water spray-off, 5 min @ 38°C, %, ASTM D 4049	7.7
Oxidation stability, 100 h @ 99°C & 758 kPa, pressure drop, kPa, ASTM D 942	12
Car wheel bearing test (accelerated) 20 h @ 160°C, leakage, g, ASTM D 4290	1.9
Corrosion prevention, 48 h @ 52°C, rating, ASTM D 1743	pass
Copper corrosion, T2 copper strip, 24 h @ 100°C, rating, ASTM D 4048	pass

These data are given as an indication of typical values and not as exact specifications.

Industry and OEM specifications

Sinopec HPXT Grease meets the performance requirements of the following industry specifications:	
Sinopec	SHRH YXY 5180-2012

Accuracy of information

Data provided in this PDS is typical and subject to change as a result of continuing product research and development. The information given was correct at the time of printing. The typical values given are subject to variations in the testing procedures and the manufacturing process may also result in slight variations. Sinopec guarantees that its lubricants meet any industry and OEM specifications referred to on this data sheet.

Sinopec cannot be held responsible for any deterioration in the product due to incorrect storage or handling. Information on best practice is available from your local distributor.

Product and environmental safety

This product should not cause any health problems when used in the applications suggested and when the guidance provided in the Material Safety Data Sheet (MSDS) is followed. Please consult the MSDS for more detailed advice on handling; MSDSs are available from your local distributor. Do not use the product in applications other than those suggested.

As with all products, please take care to avoid environmental contamination when disposing of this product. Used oil should be sent for reclamation/recycling or, if not possible, must be disposed of according to relevant government/authority regulations.

The SINOPEC trademark is registered and protected.

Issued: March 2017

© Sinopec 2017

Sinopec HPXT Grease